



No. :

Date :

DORPOL ۲۰۰۰

تاریخ:

شماره:

Properties and use

Medium reactivity unsaturated orthophthalic polyester resin, high flexibility and bending strength, excellent storage stability. For general use in hand laminating, fiber injection, injection moldings.

Form of Delivery (f.o.d)

67% in Styrene

Product Data

Viscosity mpa.s (25°C)	450-650
Acid value (mg KOH/g)	35
Nonvolatile matter	67%±۲
Density Approx. (25°C) g/cm ³	1.09
Flash point Approx. (°C)	34