



No. :

Date :

تاریخ

شماره :

DORPOL 800

Properties and use

Unsaturated polyester resin, It is mainly used for stone sticks.

Form of Delivery (f.o.d)

66% in Styrene

Product Data

Viscosity mpa.s (25°C)	550-750
Acid value (mg KOH/g)	35
Solid content	66%±1
Density Approx. (25°C) g/cm ³	1.05
Flash point Approx. (°C)	34